



# Electrodag™ 725A (6S-61)™

August 2009

## PRODUCT DESCRIPTION

Electrodag™ 725A (6S-61)™ provides the following product characteristics:

<b>Technology</b>	Thermoplastic
<b>Appearance</b>	Silver
<b>Filler Type</b>	Silver
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• Conductive</li> <li>• Process ease</li> <li>• Screen printable</li> <li>• Long shelf life</li> <li>• Good printability</li> <li>• Excellent flexibility</li> <li>• No thinning required</li> <li>• Low electrical resistance</li> <li>• Excellent adhesion strength</li> <li>• Good screen residence time</li> </ul>
<b>Cure</b>	Heat cure
<b>Application</b>	Conductive Ink
<b>Operating Temperature-Maximum</b>	100°C
<b>Typical Assembly Applications</b>	Membrane keyboards, membrane touch switches and Flexible circuits

Electrodag™ 725A (6S-61)™ is designed for use in the production of low voltage circuitry on polyester film.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content (3 hours @ 110°C), %	60 to 63
Viscosity, Brookfield, mPa·s (cP):	
Speed 20 rpm, @ 20°C	15,000 to 18,000
Density, , Kg/cm³	2,100
Theoretical coverage, m² /kg:	
@ 10µm dry coating thickness	12
Shelf Life @ 4 to 8°C, year:	
From date of qualification in original seal	1
Flash Point, Tag Closed Cup Flash Tester, °C	94

## TYPICAL SCREEN PRINTING PROCESS

<b>Emulsion Thickness</b>	
Solvent resistant emulsion, µm	10 to 40
<b>Recommended Squeegee</b>	
Shore Hardness	70 to 80
<b>Recommended Screen Type</b>	
Monofilament polyester screen, threads/cm	64 to 80
Stainless steel screen, threads/cm	68 to 130
<b>Printing Equipment Type</b>	
Manual	
Semi-automatic	
High speed reel-to-reel	

## TYPICAL CURING PERFORMANCE

### Recommended Drying Cycle

15 minutes @ 120°C

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

Dry Coating on Polyester foil, dried 15 minutes @ 120°C

### Physical Properties

Adhesion, grade	5B
Cohesion test (resistance change), %	<3

### Electrical Properties

Sheet Resistivity @ 25µm, ohms/sq	0.008 to 0.014
-----------------------------------	----------------

## GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

## DIRECTIONS FOR USE

1. Mix thoroughly with plastic spatula or mechanical stirrer from bottom of container, careful not to whip air in to the product. Using a plastic spatula will decrease the possibility of introducing plastic grindings from the container sidewalls into the product, which could damage the screen.
2. Bring product to room temperature prior to use.
3. Electrodag™ 725A (6S-61)™ is supplied ready for use. Should thinning become necessary, dilute 1 to 3% by weight with Electrodag™ DBE.

### Clean-up

To clean screen and equipment, use Methyleneethylketone (MEK) or similar solvents

### Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

### Optimal Storage: 4 to 8 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.



**Not for product specifications**

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**Conversions**

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{inches}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{N/mm}^2 \times 145 = \text{psi}$$

$$\text{MPa} \times 145 = \text{psi}$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

**Note**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0