



HYSOL US1150

June 2012

PRODUCT DESCRIPTION

HYSOL US1150 provides the following product characteristics:

Technology	Urethane
Appearance - Part A	Brown
Appearance - Part B	Black
Appearance (cured)	Black
Components	Two component - requires mixing
Mix Ratio, by volume - Part A: Part B	1 : 4
Mix Ratio, by weight - Part A: Part B	21 : 100
Cure	Room temperature cure
Application	Potting and Encapsulating

HYSOL US1150 is an extended polybutadiene/MDI base, mineral filled, medium hardness, ambient cure urethane encapsulant/sealant. This material can be used for potting electronics or devices for protection against environmental hazards. It exhibits very little hardness increase when cooled to -75°C. It can be used for devices in the telecommunications and automotive industries. HYSOL US1150 meets UL 94V-0 rating. The 1 to 4 volume mix ratio makes meter-mix dispensing convenient.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties

Density, 25 °C, g/cm ³	1.21
Viscosity, Brookfield - RVF, 25 °C, cP:	
Spindle 2, speed 20 rpm,	90

Part B Properties

Density, 25 °C, g/cm ³	1.46
Viscosity, Brookfield - RVF, 25 °C, cP:	
Spindle 2, speed 20 rpm	13,000

Mixed Properties

Density, 25 °C, g/cm ³	1.44
Viscosity, Brookfield - RVF, 25 °C, cP:	
Spindle 2, speed 20 rpm,	3,500
Working Time, 140 g mass, , minutes	60

TYPICAL CURING PERFORMANCE

Gel Time

140 gm mass, 90 to 120 minutes @ 25°C

Recommended Cure

24 to 48 hours @ 25°C

Alternative Cure Schedule

2 to 4 @ 60 to 85°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Shore Hardness , Durometer A	60
24 Hour Water Moisture Absorption, %	<0.2
Glass Transition Temperature, °C	-60
Coefficient of Linear Thermal Expansion, ppm/°C:	
Alpha 1, @ -20 to 0 °C	140
Alpha 2, @ 10 to 50 °C	158
Linear Shrinkage, ASTM D792, %	<1.0
Coefficient of Thermal Conductivity, W/(m-K)	0.486

Electrical Properties

Volume Resistivity , ohm-cm:	
@ 25 °C	2.96×10 ¹³
@ 85 °C	5.32×10 ¹¹
Surface Resistivity, ohms:	
@ 25 °C	3.02×10 ¹⁴
@ 85 °C	4.27×10 ¹²
Dielectric Strength, 20 mil thickness, volts/mil	950
Dielectric Constant / Dissipation Factor:	
@ 25 °C:	
@ 100 Hz	4.89/0.05
@ 1 KHz	5.33/0.07
@ 85 °C:	
@ 100 Hz	4.91/0.06
@ 1 KHz	5.16/0.03

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Note: Before using this product please purge approximately 30 ml. of material prior to application. Discard purged material in accordance with the Material Safety Data Sheet. A video instruction is available upon request.



Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Liquid Storage - Liquids should be stored at 23°C or below, in closed containers. If stored below 23°C, the material MUST be allowed to come to room temperature, in the sealed container, to avoid moisture contamination.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation and its affiliates ("Henkel") specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel products. Henkel specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

All trademarks in this document are trademarks and/or registered trademarks of Henkel in the US and elsewhere.

Reference 1.3