



HYSOL[®] US1750[™]

September 2007

PRODUCT DESCRIPTION

HYSOL[®] US1750[™] provides the following product characteristics:

Technology	Urethane
Appearance (Part A)	Clear
Appearance (Part B)	Clear
Appearance (cured)	Clear
Components	Two component - requires mixing
Mix Ratio, by volume - Part A: Part B	1 : 1
Mix Ratio, by weight - Part A: Part B	50.5 : 49.5
Cure	Room temperature cure
Application	Potting and Encapsulating

HYSOL[®] US1750[™] elastomeric polyurethane, is a water-white, clear, medical grade, fast gel potting material. It is ideal for blood heat exchanger, dialyzer and oxygenator units.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties

Density, @ 25 °C, g/cm ³	1.08
Viscosity, Brookfield - RVF, 25 °C, cP:	
Spindle, speed r/min	350

Part B Properties

Density, @ 25 °C, g/cm ³	1.06
Viscosity, Brookfield - RVF, 25 °C, cP:	
Spindle, speed r/min	370

Mixed Properties

Gel Time, 100 gm mass @ 45 °C, minutes	5 to 7
Drystick Gel 25 gm mass, @ 25 °C, minutes	60 to 70
Viscosity, Brookfield - RVF, 25 °C, cP:	
Spindle, speed r/min	510

TYPICAL CURING PERFORMANCE

Recommended Curing Conditions

16 hours @ 25 °C (Recommended cure)	
1 hour @ 50 °C (Alternate cure)	

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Shore Hardness, Durometer A	78
Density, @ 25 °C, g/cm ³	1.07
Tensile Strength, psi	541
Tensile Elongation, %	198
Glass Transition Temperature, °C	30
Coefficient of Linear Thermal Expansion, ppm/°C:	
Alpha 1, @ -20 to 0 °C	137
Alpha 2, @ 60 to 80 °C	235
Thermal Conductivity, W/mk	0.19

Electrical Properties:

Dielectric Strength, 20 mils thickness, volts/mil	1,292
Surface Resistivity, ohms @ 25°C	5.66×10 ¹³
Volume Resistivity, ohm/cm @ 25°C	1.06×10 ¹³
Dielectric Constant / Dissipation Factor @ 25°C:	
100 Hz	6.41 / 0.072
1 kHz	5.99 / 0.067
100 kHz	5.01 / 0.056

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Note: Before using this product please purge approximately 30 ml. of material prior to application. Discard purged material in accordance with the Material Safety Data Sheet. A video instruction is available upon request.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Liquid Storage - Liquids should be stored at 23°C or below, in closed containers. If stored below 23°C, the material MUST be allowed to come to room temperature, in the sealed container, to avoid moisture contamination.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm ² x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·m x 0.738 = lb·ft
N·mm x 0.142 = oz·in
mPa·s = cP

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose



Technologies

methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.1